

LG-770 Phosphate Laser Glass

For High Energy Applications


Neodymium Laser Properties	
Emission Peak, λ [nm]	1052.7
Emission Width, $\Delta \lambda_{em}$ [nm]	25.4
Radiative Lifetime T_{Rad} [μ sec]	350
Emission Cross Section σ_{em} [$10^{-20}cm^2$]	3.9
*Quenching Constant-Zero Concentration Lifetime, τ_0 [μ sec]	372
*Quenching Constant-Q Factor, Q [$10^{20}cm^{-3}$]	8.8

*Lifetime as a function of neodymium content is approximated by: $T = \tau_0 / (1 + (Nd / Q)^2)$,
Nd=Nd concentration in 10^{20} ions/cm³

Optical Properties			
n_d			1.5086
v_d			68.40
n_{633nm}			1.5070
n_{1054nm}			1.4996
Nonlinear Refractive Index at 1054nm, n_2 [10^{-13} esu]			1.02
Stress-Optic Coefficient, K (588nm, 22°C)[$10^{-6}mm^2/N$]			2.10
Stress-Optic Coefficient, $-K_{par}$ (632.8nm, 25°C)[$10^{-6}mm^2/N$]			2.20
Stress-Optic Coefficient, $-K_{per}$ (632.8nm, 25°C)[$10^{-6}mm^2/N$]			3.90
Temperature Coefficient of Refractive Index, dn/dT_{rel} (1060nm, 20-40°C) [$10^{-6}/^\circ C$]			-4.7
Temperature Coefficient of Optical Pathlength, $W = \alpha_{20-40^\circ C} (n-1) + dn/dT$ [$10^{-6}/^\circ C$]			1.1
Sellmeier Coefficients			
B1	1.03692728	C1	0.00577291
B2	0.21105327	C2	0.01976189
B3	0.77362466	C3	101.422203
Attenuation Coefficient [cm. ⁻¹]			
400nm	≤ 0.20	3000nm	≤ 0.80
1054nm	≤ 0.0015	3333nm	≤ 2.00

LG-770 is an aluminum-phosphate based glass with a high cross section for stimulated emission, extremely low nonlinear refractive index, and good athermal characteristics. This glass was initially developed for the US DOE National Ignition Facility and French CEA Project Laser Megajoule. The development and the advantages of this glass are discussed in "Laser and thermo-physical properties of Nd-doped phosphate glasses" Proc SPIE, Vol 1761, 162-173 (1992).


LG-770 Fluorescence Lifetime




Physical Properties	
Density, ρ [g/cm ³]	2.585
Thermal Conductivity (25°C), K [W/m•K]	0.57
Thermal Conductivity (90°C), K [W/m•K]	0.63
Young's Modulus, E [GPa]	47.29
Poisson's Ratio, ν	0.253
Fracture Toughness, K_{Ic} [MPa•m ^{1/2}]	0.48
Knoop Hardness, $HK_{0.1/20}$	330
Heat Capacity (25°C), C_p [J/g°C]	0.77
Thermal Diffusivity (25°C), σ [$10^{-7}m^2/sec$]	2.86
Thermal Expansion, $\alpha_{20-300^\circ C}$ [$10^{-7}/^\circ C$]	133.6
Thermal Expansion, $\alpha_{20-40^\circ C}$ [$10^{-7}/^\circ C$]	116.1
Transformation Temperature, T_g [°C]	461

LG-770 Phosphate Laser Glass

For High Energy Applications



Chemical Properties	
Weight Loss in 50°C Water [mg/(cm ² •day)]	0.040
Acid Resistance SR pH=0.3 at 25°C	3.0
Alkali Resistance AR pH=12 at 50°C	4.0
Staining Resistance FR pH=4.6 100h at 25°C	0
Climatic Resistance CR Water Vapor at 40-50°C for 30 h	3



For more information please contact:

Advanced Optics
SCHOTT North America, Inc.
 400 York Avenue
 Duryea, PA 18642
 USA

Phone: +1 (0) 570/457-7485
 Fax: +1 (0) 570/457-7330
 info.optics@us.schott.com
 www.us.schott.com/advanced_optics

SCHOTT
 glass made of ideas