



SCHOTT Dental Glass Ceramics


Product Information

SCHOTT's devitrified dental glass ceramic powders will provide additional benefits for your composites.

Advantages

Expertise in special glass technology

- Glass ceramics have a very low CTE and high glass transition temperature due to its partly crystalline structure
- These materials can have a positive influence on tooth abrasion
- They also can improve polishability
- Refractive indices have been designed to result in one radiolucent and one radiopaque glass ceramic product variation



Glass ceramics with their refractive indices

Materials Data:

		GM31684	GM31685
Expansion coefficient (-30/+70 °C)	10 ⁻⁶ /K	Approx. 1	Approx. 1
Index of refraction n _d		1.58	1.53
Density	g/cm ³	2.9	2.6
Transformation temperature (ISO7884-8)	°C	> 800	> 800
Radiopacity (acc.ISO 4049) as thickness of aluminium equal to 2-mm thick glass material	mm	4.4 (220%)	1.5 (75%)
Hydrolytical resistance (DIN ISO 719)		Class 1	Class 1
Composition (approx. values) [weight-%]	SiO ₂	50	60
	Al ₂ O ₃	20	20
	ZnO	1	1
	P ₂ O ₅	5	-
	La ₂ O ₃	10	-
	ZrO ₂	5	5
	Li ₂ O	5	5
	MgO	-	5
	K ₂ O	1	1
	Ta ₂ O ₅	1	1

Grain sizes

Type	Description	Size	Grain size		Approx. Surface [m ² /g]
			d ₅₀ [µm]	d ₉₉ [µm]	
K	Standard grind	K1	30 ± 10	≤ 150	-
		K2	16 ± 4	≤ 100	-
		K3	10 ± 2	≤ 63	-
		K4	7 ± 1	≤ 40	-
		K5	5 ± 1	≤ 40	0.5
		K6	3 ± 1	≤ 40	0.6
SM	Special grind with narrow distribution	SM 3.5	3.5 ± 1	≤ 13	2

For more information:

SCHOTT Electronic Packaging
 A Division of SCHOTT North America, Inc.
 122 Charlton Street
 Southbridge, MA 01550
 USA

Phone: +1 508 765-3370
 Fax: +1 508 765-3377
 epackaging@us.schott.com
 www.us.schott.com/epackaging

SCHOTT
 glass made of ideas