Glass GS10

Technical Data

GlassType/Application	Transition glass. SCHOTT glass no. 8213

Physical Data (approx. value)

Coefficient of mean linear thermal expansion		
α(20°C; 300°C) (ISO 7991)	1.25	$10^{-6}K^{-1}$
Glass temperature at viscosity η in dPa·s		
$10^{14.7}$ (strain point) (ISO 7884-4)	635	°C
$10^{13.2}$ (annealing point) (ISO 7884-4)	725	°C
$10^{7.6}$ (softening point) (ISO 7884-3)	1195	°C
10^{4} (working point) (ISO 7884-3)	1710	°C
Density (DIN 66137-2)	2.17	g/cm³
Log of the electric volume resistivity (Ω·cm)		
at 250°C	10.5	
at 350°C	8.9	
t_{k100}	420	°C

Chemical Composition (components in approx. weight %)

SiO_2	B_2O_3	Al_2O_3	BaO	Fe_2O_3
85	10	4.5	0.5	<0.1

The heavy metal content for the elements lead, cadmium, mercury and hexavalent chromium is below 100 ppm.

SCHOTT
glass made of ideas