

P-LASF51 810409.458

$n_d = 1,81000$	$v_d = 40,93$	$n_F - n_C = 0,019792$
$n_e = 1,81470$	$v_e = 40,68$	$n_F' - n_C' = 0,020025$

Brechzahlen		
	λ [nm]	
$n_{2325,4}$	2325,4	1,76437
$n_{1970,1}$	1970,1	1,77145
$n_{1529,6}$	1529,6	1,77923
$n_{1060,0}$	1060,0	1,78815
n_i	1014,0	1,78927
n_e	852,1	1,79413
n_f	706,5	1,80082
n_C	656,3	1,80411
$n_{C'}$	643,8	1,80504
$n_{632,8}$	632,8	1,80591
n_D	589,3	1,80983
n_d	587,6	1,81000
n_e	546,1	1,81470
n_F	486,1	1,82390
$n_{F'}$	480,0	1,82506
n_g	435,8	1,83512
n_h	404,7	1,84467
n_i	365,0	1,86148
$n_{334,1}$	334,1	1,88043
$n_{312,6}$	312,6	
$n_{296,7}$	296,7	
$n_{280,4}$	280,4	
$n_{248,3}$	248,3	

Konstanten der Dispersionsformel	
B_1	1,84568806
B_2	0,339001600
B_3	1,324189210
C_1	0,00988495571
C_2	0,0378097402
C_3	97,8415430

Konstanten der Formel für dn/dT	
D_0	7,79E-06
D_1	1,10E-08
D_2	-2,03E-11
E_0	7,86E-07
E_1	8,78E-10
λ_{TK} [μm]	0,215

Temperaturkoeffizienten der Lichtbrechung						
[°C]	$\Delta n_{rel}/\Delta T$ [$10^{-6}/K$]			$\Delta n_{abs}/\Delta T$ [$10^{-6}/K$]		
	1060.0	e	g	1060.0	e	g
-40/-20	6,8	8,3	9,9	4,4	5,9	7,3
+20/+40	6,9	8,7	10,4	5,4	7,1	8,8
+60/+80	7,1	8,9	10,8	5,9	7,7	9,6

Reintransmissionsgrad τ_i		
λ [nm]	τ_i [10mm]	τ_i [25mm]
2500	0,530	0,200
2325	0,780	0,530
1970	0,950	0,880
1530	0,992	0,981
1060	0,999	0,998
700	0,998	0,995
660	0,997	0,993
620	0,997	0,992
580	0,997	0,992
546	0,997	0,992
500	0,995	0,987
460	0,990	0,975
436	0,985	0,963
420	0,980	0,950
405	0,971	0,930
400	0,967	0,920
390	0,954	0,890
380	0,930	0,830
370	0,880	0,720
365	0,840	0,650
350	0,660	0,350
334	0,250	0,030
320	0,010	
310	0,000	
300		
290		
280		
270		
260		
250		

Farbcode	
$\lambda_{80} / \lambda_{5}$	39/33

(* = λ_{70}/λ_5)

Bemerkungen
zum Blankpressen geeignet

Relative Teildispersionen	
$P_{s,t}$	0,2453
$P_{C,s}$	0,5045
$P_{d,C}$	0,2976
$P_{e,d}$	0,2376
$P_{g,F}$	0,5670
$P_{i,h}$	0,8491
$P'_{s,t}$	0,2425
$P'_{C,s}$	0,5450
$P'_{d,C'}$	0,2477
$P'_{e,d}$	0,2348
$P'_{g,F'}$	0,5024
$P'_{i,h}$	0,8392

Abweichung relativer Teildispersionen ΔP von der "Normalgeraden"	
$\Delta P_{C,t}$	0,0107
$\Delta P_{C,s}$	0,0062
$\Delta P_{F,e}$	-0,0021
$\Delta P_{g,F}$	-0,0080
$\Delta P_{i,g}$	-0,0494

Sonstige Eigenschaften	
$\alpha_{-30/+70^\circ\text{C}}$ [$10^{-6}/K$]	6,0
$\alpha_{+20/+300^\circ\text{C}}$ [$10^{-6}/K$]	7,4
T_g [°C]	526
T_{10}^{13} [°C]	534
$T_{10}^{7,6}$ [°C]	629
c_p [J/(g·K)]	0,560
λ [W/(m·K)]	0,870
AT [°C]	570
ρ [g/cm ³]	4,58
E [10^3 N/mm ²]	119
μ	0,299
K [10^{-6} mm ² /N]	2,32
$HK_{0,1/20}$	722
Abrasion Aa	66
CR	1
FR	1
SR	51,3
AR	1
PR	2,2
SR-J	3
WR-J	1