

## N-BALF4 580539.311

$n_d = 1.57956$	$v_d = 53.87$	$n_F - n_C = 0.010759$
$n_e = 1.58212$	$v_e = 53.59$	$n_F' - n_C' = 0.010863$

Refractive Indices		
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.55068
$n_{1970.1}$	1970.1	1.55577
$n_{1529.6}$	1529.6	1.56124
$n_{1060.0}$	1060.0	1.56707
$n_t$	1014.0	1.56776
$n_s$	852.1	1.57065
$n_f$	706.5	1.57447
$n_C$	656.3	1.57631
$n_{C'}$	643.8	1.57683
$n_{632.8}$	632.8	1.57731
$n_D$	589.3	1.57946
$n_d$	587.6	1.57956
$n_e$	546.1	1.58212
$n_F$	486.1	1.58707
$n_{F'}$	480.0	1.58769
$n_g$	435.8	1.59301
$n_h$	404.7	1.59799
$n_i$	365.0	1.60658
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

Constants of Dispersion Formula	
$B_1$	1.31004128
$B_2$	0.142038259
$B_3$	0.964929351
$C_1$	0.00796596450
$C_2$	0.0330672072
$C_3$	109.1973200

Constants of Formula for $dn/dT$	
$D_0$	5.33E-06
$D_1$	1.47E-08
$D_2$	-1.58E-11
$E_0$	5.75E-07
$E_1$	6.58E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.195

Temperature Coefficients of the Refractive Index						
[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.1	4.9	5.6	2.0	2.7	3.4
+20/+40	4.2	5.1	6.0	2.9	3.7	4.6
+60/+80	4.4	5.4	6.4	3.4	4.3	5.3

Internal Transmittance $\tau_i$		
$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.800	0.580
2325	0.890	0.740
1970	0.967	0.920
1530	0.994	0.984
1060	0.997	0.993
700	0.999	0.997
660	0.998	0.995
620	0.998	0.995
580	0.998	0.996
546	0.998	0.995
500	0.997	0.993
460	0.994	0.986
436	0.993	0.983
420	0.992	0.981
405	0.988	0.970
400	0.985	0.964
390	0.976	0.940
380	0.959	0.900
370	0.920	0.820
365	0.890	0.750
350	0.680	0.380
334	0.160	
320		
310		
300		
290		
280		
270		
260		
250		

Color Code	
$\lambda_{80} / \lambda_5$	37/33

Remarks	

Relative Partial Dispersion	
$P_{s,t}$	0.2687
$P_{C,s}$	0.5265
$P_{d,C}$	0.3019
$P_{e,d}$	0.2382
$P_{g,F}$	0.5520
$P_{i,h}$	0.7986
$P'_{s,t}$	0.2661
$P'_{C,s}$	0.5689
$P'_{d,C'}$	0.2515
$P'_{e,d}$	0.2359
$P'_{g,F'}$	0.4897
$P'_{i,h}$	0.7909

Deviation of Relative Partial Dispersion $\Delta P$ from the normal line	
$\Delta P_{C,t}$	-0.0053
$\Delta P_{C,s}$	-0.0019
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0012
$\Delta P_{i,g}$	-0.0114

Other Properties	
$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$T_g$ [°C]	578
$T_{10}^{13}$ [°C]	584
$T_{10}^{7.6}$ [°C]	661
$c_p$ [J/(g·K)]	0.690
$\lambda$ [W/(m·K)]	0.850
$\rho$ [g/cm <sup>3</sup> ]	3.11
$E$ [ $10^3$ N/mm <sup>2</sup> ]	77
$\mu$	0.245
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.01
$HK_{0.1/20}$	540
HG	2
CR	1
FR	0
SR	1
AR	1
PR	1